

Alternatives to C-33 Sand

Exploring Options for Septic Drainfields

Disclaimer

OPINIONS PRESENTED IN THIS PRESENTATION ARE
THE PRESENTER'S AND DO NOT REFLECT THE
OPINONS OF NOWRA

Introduction

THIS PRESENTATION EXAMINES ALTERNATIVES TO C-33 SAND FOR SEPTIC DRAINFIELDS. IT EMPHASIZES THE SIGNIFICANCE OF CHOOSING SUITABLE AGGREGATES, CONSIDERS ENVIRONMENTAL IMPACTS, AND INVESTIGATES INNOVATIVE SOLUTIONS TO IMPROVE DRAINFIELD PERFORMANCE.

agenda



- About C-33 Sand
- Overview of Aggregates
- Importance in Septic Systems
- Environmental Impact
- Summary

C-33 Sand Overview



- **Grading and Sieve Analysis:** C-33 sand must meet a specific **gradation** as defined by ASTM standards. This means it has a controlled distribution of particle sizes, with very little "fines" (silt and clay).
- **Particle Shape and Cleanliness**
- **High Permeability**
- **Support for Aerobic Conditions**



Optimal for Drainage
and Aeration

Understanding C-33 Sand

ASTM Guidelines

C-33 Sand must meet specific guidelines set by the ASTM, ensuring a consistent and reliable material


Optimal Structure

Uniform particle size and coarse texture allow wastewater to drain at a controlled rate while providing ample space for air circulation


High Permeability

The porosity and permeability of C-33 sand are key to its function. The controlled particle size distribution creates a network of interconnected pores that allows water to drain effectively while still providing enough resistance to ensure proper treatment time.

ASTM C33



C-33 Sand



Aggregate Types



CRUSHED STONE



RECYCLED GLASS



RECYCLED
CONCRETE

Overview of Aggregate Types



Crushed Stone

Durable alternative with excellent drainage properties



Recycled Concrete

Sustainable option repurposing construction waste



Recycled Glass

Innovative material with properties similar to C-33 sand

Various aggregate materials can serve as replacements for C-33 sand. Each option comes with distinct physical and chemical properties that influence system performance. Understanding these characteristics is crucial for effective septic system performance.



Crushed Stone

- **Improved Drainage:** The larger, angular particles of crushed stone create a high-void-space aggregate. This allows for excellent permeability and faster effluent drainage compared to sand, reducing the risk of a clogged or waterlogged drain field.
- **Superior Durability:** Crushed stone is an incredibly durable, non-compressible material. Its lack of fines (silt and clay) and resistance to breakdown ensure it won't settle or become clogged over time, contributing to the long-term performance and lifespan of the septic system.

Recycled Concrete

- **Environmental Benefit:** RCA reduces landfill waste and the need for new mining, making it a sustainable choice.
- **Excellent Drainage:** Its angular shape and high void content allow for superior water flow, which helps prevent clogs.
- **Cost-Effective:** Often cheaper and locally sourced, RCA can significantly reduce project costs.
- **Potential Drawbacks:** Can contain contaminants and has an alkaline pH, which might affect the soil. Local regulations may also limit its use.





Recycled Crushed Glass

- **Environmental Impact:** A sustainable choice that reduces landfill waste and the need to mine natural sand.
- **Superior Drainage:** Its sharp, non-porous particles create larger voids, allowing for faster and more efficient wastewater drainage.




Testing

Testing for TSS and the Particle size analysis



Partical Size Gradation for tested materials compared to ASTM specification



Importance of the Aggregate in the Septic System

- ▶ The choice of aggregate significantly impacts the drainage capacity, longevity, and overall efficiency of septic systems. Proper alternatives ensure better water percolation, prevent clogging, and reduce the risk of environmental contamination. Selecting the right material is essential for proper waste management practices.

Testing Results

- The Fine Crushed Glass out performed the C-33 sand on the TSS testing
- The fine crush glass closely matched the limits of C-33

Using recycled materials, for example, can reduce landfill waste and lower carbon footprints. It is vital to evaluate how different aggregates interact with the ecosystem, ensuring that they do not leach harmful substances into groundwater, thereby protecting public health and the environment.

Environmental Impact



Conclusion

- **C-33 Sand:** Remains the **gold standard** for septic systems due to its reliable, standardized grading and proven performance in providing optimal filtration and biological treatment.
- **Alternative Aggregates:** Recycled aggregates, such as **crushed stone, concrete, and glass**, offer promising alternatives. They can be more **sustainable and cost-effective**, often providing superior drainage and durability compared to traditional sand.
- **The Key Takeaway:** While each alternative has unique benefits—from the excellent drainage of crushed stone to the environmental advantages of recycled materials—their use requires **careful consideration of their specific properties**, including potential contaminants and regulatory requirements, to ensure the long-term health and performance of the septic system.

Thank You

JIMMY BELL

JBELL@ELJEN.COM